



Dynalife® L-EP

Dynalife L-EP is a multipurpose, extreme-pressure lithium grease developed for use in a wide variety of industrial and automotive applications. It is a versatile, general-purpose grease recommended for use in applications where operating temperatures and loads are moderate. It is available in six grades to cover a wide range of applications.

Dynalife L-EP is manufactured with high-quality base oils thickened with lithium 12-hydroxystearate soap. It is fortified with extreme-pressure and antiwear additives plus rust and oxidation inhibitors. It has good load-carrying capacity for protection against wear, good oxidation resistance for long service life, protects metal parts against rust and corrosion, and is resistant to water washout. It has good resistance to structural breakdown and will not soften excessively during high-speed operation in rolling-element bearings. It forms a good seal to help minimize bearing contamination.

Applications

- Plain and rolling-element bearings in compressors, fans, centrifugal pumps and other industrial equipment where operating temperatures and loads are moderate
- Chassis parts, universal joints and water pumps on passenger cars, light trucks and other mobile equipment
- Track rollers, commercial lawn mowers, crushers and vibrating screens (semifluid grades)
- Underground mining machinery and other enclosed gearboxes where oil leakage is a problem (semifluid grades)
- Wheel bearings of passenger cars equipped with drum brakes
- Centralized grease lubrication systems
- General-purpose shop/industrial grease

Features/Benefits

- Multipurpose grease for use in a wide variety of applications
- Good extreme-pressure and antiwear properties
- Good shear stability
- Good oxidation resistance and thermal stability
- Protects against rust and corrosion
- Resists water washout
- Good low-temperature pumpability
- Suitable for use in centralized lube systems

**Multipurpose,
Extreme-Pressure
Lithium Grease**

Customer Service
Number:
1-714-556-0808

Email Address:
Anthony@
Intraoil.com



Dynalife® L-EP

Typical Properties

NLGI Grade	000	00	0	1	2	3
Thickener	Lithium	Lithium	Lithium	Lithium	Lithium	Lithium
Color	Amber	Amber	Amber	Amber	Amber	Amber
Dropping Point,						
°C	—	—	177	177	177	177
°F	—	—	350	350	350	350
Density, lbs/gal	7.44	7.44	7.44	7.44	7.44	7.44
Penetration, Worked (60 strokes),						
ASTM D217	445-475	400-430	355-385	310-340	265-295	220-250
Texture	Semifluid	Semifluid	Soft-Smooth	Smooth	Smooth	Smooth
Four-Ball EP, ASTM D2596,						
Weld Load, kgf	250	250	250	250	250	250
Four-Ball Wear, ASTM D2266,						
Scar Diameter, mm	0.60	0.45	0.45	0.45	0.45	0.45
Oxidation Stability, ASTM D942, 100 hrs,						
Pressure Drop, psi (kPa)	—	—	—	5 (35)	5 (35)	5 (35)
Rust Prevention, ASTM D1743	Pass	Pass	Pass	Pass	Pass	Pass
Timken OK Load, ASTM D2509, lb	40	40	40	40	40	40
Base Oil Properties:						
Viscosity (with polymer),						
cSt @ 40°C	195	195	195	195	195	195
cSt @ 100°C	16.5	16.5	16.5	16.5	16.5	16.5
SUS @ 100°F	1,000	1,000	1,000	1,000	1,000	1,000
SUS @ 210°F	86	86	86	86	86	86
Viscosity Index	80	80	80	80	80	80
Usable Temperature Range,						
°C	-21 to 107	-21 to 107	-18 to 121	-18 to 124	-18 to 143	-9 to 143
°F	-5 to 225	-5 to 225	0 to 250	0 to 255	0 to 290	15 to 290

Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3.conocophillips.com/NetMSDS>.

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

Copyright © 2010 ConocoPhillips Company. The ConocoPhillips logo, Conoco, the Conoco logo, Phillips 66, the Phillips 66 logo, 76 and the 76 logo are trademarks of ConocoPhillips Company in the U.S.A. and other countries.