



Megaplex® XD5

Megaplex XD5 is a high-performance, multipurpose, extreme-pressure (EP) lithium complex grease developed to satisfy the severe lubrication requirements of mining and off-road equipment manufactured by Caterpillar, Terex, Komatsu Dresser and others. It is particularly recommended for use in AC and DC electric-drive haul trucks, cranes, scrapers, shovels and drag lines operating in severe service under heavy or shock loads.

Megaplex XD5 is manufactured with high-quality base oils thickened with lithium complex soap. It is fortified with extreme-pressure and antiwear additives, 5% molybdenum disulfide (moly), a tackifier, and rust and oxidation inhibitors to provide excellent wear protection as well as excellent corrosion protection and resistance to water washout in equipment operating under wet conditions and/or high temperatures and subject to heavy or shock loading.

Megaplex XD5 Grades No. 0 and No. 1W are formulated with lower-viscosity base oils than the other two grades for better pumpability at low ambient temperatures.

Applications

- Chassis parts and wheel bearings on mining and other off-highway equipment
- Caterpillar 5100 and 5200 series hydraulic excavator mining shovels
- Terex haul trucks
- Heavily loaded plain and rolling-element bearings in industrial enclosed gear drives where the manufacturer specifies a high-temperature, extreme-pressure grease with 5% moly

Megaplex XD5 meets the requirements of the following OEM specification:

- Caterpillar Multipurpose Molybdenum Grease (MPGM)

Features/Benefits

- Meets Caterpillar and Terex requirements for 5% moly grease
- High dropping point (500°F)
- High load-carrying capacity
- Excellent wear protection
- Excellent resistance to water washout

**Extreme-Pressure
Lithium Complex
Grease With
5% Moly For Mining
& Off-Road
Equipment**

Customer Service
Number:
1-714-556-0808

Email Address:
Anthony@
Intraoil.com



- Excellent resistance to separation
- Protects against rust and corrosion

Megaplex® XD5

Typical Properties

NLGI Grade	0	1W	1	2
Thickener	Lithium Complex	Lithium Complex	Lithium Complex	Lithium Complex
Color	Gray-Black	Gray-Black	Gray-Black	Gray-Black
Dropping Point, °C (°F)	260 (500)	260 (500)	260 (500)	260 (500)
Density, lbs/gal	7.92	7.92	7.96	7.99
Penetration, Worked (60 strokes),				
ASTM D217	355-385	310-340	310-340	265-295
Texture	Tacky	Tacky	Tacky	Tacky
Molybdenum Disulfide, wt %	5	5	5	5
Four-Ball EP, ASTM D2596, Weld Load, kgf	315	315	315	400
Four-Ball Wear, ASTM D2266,				
Scar Diameter, mm	0.50	0.65	0.50	0.50
Oxidation Stability, ASTM D942, 100 hrs.,				
Pressure Drop, psi (kPa)	4 (28)	4 (28)	4 (28)	4 (28)
Rust Prevention, ASTM D1743	Pass	Pass	Pass	Pass
Timken OK Load, ASTM D2509, lb	55	50	55	55
Base Oil Properties:				
Viscosity (with polymer),				
cSt @ 40°C	180	140	245	470
cSt @ 100°C	13.7	13.0	19.0	30.0
SUS @ 100°F	962	739	1,304	2,526
SUS @ 210°F	75	72	97	147
Viscosity Index	60	70	76	92
Usable Temperature Range,				
°C	-23 to 204	-28 to 93	-20 to 204	-12 to 204
°F	-10 to 400	-20 to 200	-5 to 400	10 to 400

Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3.conocophillips.com/NetMSDS>.

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

Copyright © 2011 ConocoPhillips Company. The ConocoPhillips logo, Conoco, the Conoco logo, Phillips 66, the Phillips 66 logo, 76 and the 76 logo are trademarks of ConocoPhillips Company in the U.S.A. and other countries.